

I hereby certify that this paper is being deposited with the United States Postal Service as Express Mail in an envelope addressed to: Asst. Comm. for Patents, Washington, D.C. 20231, on this date.

October 12, 2001
Date

Daniel Arnan
Express Mail Label No.:
EL846162806US

SPECIFICATION

TO ALL WHOM IT MAY CONCERN:

BE IT KNOWN THAT WE, Maki Maeda, a citizen of Japan residing at Kawasaki, Japan, Hiroto Takeshita, a citizen of Japan residing at Kawasaki, Japan, Takuya Uzumaki, a citizen of Japan residing at Kawasaki, Japan and Atsushi Tanaka, a citizen of Japan residing at Kawasaki, Japan have invented certain new and useful improvements in

MAGNETIC RECORDING MEDIUM USING A PERPENDICULAR
MAGNETIC FILM HAVING A tBr NOT EXCEEDING
ONE-FIFTH OF A tBr OF AN IN-PLANE MAGNETIC FILM

of which the following is a specification : -

TITLE OF THE INVENTION

MAGNETIC RECORDING MEDIUM USING A
PERPENDICULAR MAGNETIC FILM HAVING A tBr NOT
EXCEEDING ONE-FIFTH OF A tBr OF AN IN-PLANE MAGNETIC
5 FILM

BACKGROUND OF THE INVENTION

1. Field of the Invention

The present invention generally relates to
10 a magnetic recording medium, and, more particularly,
to a magnetic recording medium used in a magnetic
recording and reproducing device employed as an
external memory device for an information processing
device such as a computer.

15 2. Description of the Related Art

Conventionally, in regard to a recording
layer of a magnetic recording medium such as a hard
disk, a technology of combining a perpendicular
magnetic film and an in-plane magnetic film has been
20 a frequently studied issue. For example, Japanese
Laid-Open Patent Application No. 11-283229 discloses
a recording method, in which a perpendicular
magnetic film is formed thick, and a recording is
performed to the perpendicular magnetic film by
25 using a magnetic head for use in an in-plane
recording. This recording method provides an
advantage of not necessitating a waveform processing,
because this method can obtain a reproduction
waveform of the in-plane-recording type, despite
30 being a recording method for a perpendicular
magnetic film.

Additionally, Japanese Laid-Open Patent
Application No. 5-189737 discloses a method of
combining two types of hard magnetic orientation
35 films (a perpendicular magnetic film and an in-plane
magnetic film) in which magnetic reversal modes
become a domain-wall-transition type and a magnetic-

rotation type, respectively, at transition positions (magnetic reversal positions) in a recording state. This method is supposed to contribute to improving an overwrite property and increasing an S/N ratio.

5 With respect to a magnetic recording medium of a composite type combining a perpendicular magnetic film and an in-plane magnetic film as above, many proposals have been made in regard to a method to perform a recording to the perpendicular magnetic
10 film. However, none of these proposals has made the magnetic recording medium satisfactory enough to be used in a practical level.

 Thereupon, with respect to such a magnetic recording medium of a composite type using a
15 perpendicular magnetic film and an in-plane magnetic film, there has recently been a proposal that the in-plane magnetic film be used to function as a recording layer, and the perpendicular magnetic film be used as an auxiliary film to enhance the function
20 of the in-plane magnetic film. It is pointed out that combining the perpendicular magnetic film with the in-plane magnetic film forms a horseshoe magnetization mode that causes a return current in a magnetic field from the in-plane magnetic film, and
25 thus, this magnetic recording medium can achieve an increase in output and a decrease in noise so as to perform a high-density recording.

 However, the above-mentioned composite magnetic recording medium using the in-plane
30 magnetic film as a recording layer has problems of the occurrence of noises due to a diamagnetic field at a transition position of the in-plane magnetic film, and a distortion in a reproduction waveform as a result of combining the perpendicular magnetic
35 film to the in-plane magnetic film. So far, no composite magnetic recording medium using the in-plane magnetic film as a recording layer has been

devised to have a preferable structure that solves these problems.

SUMMARY OF THE INVENTION

5 It is a general object of the present invention to provide an improved and useful magnetic recording medium in which the above-mentioned problems are eliminated.

10 A more specific object of the present invention is to provide a magnetic recording medium of a composite type having a perpendicular magnetic film combined with an in-plane magnetic film used as a recording layer so as to decrease noises and prevent a distortion in a reproduction waveform.

15 In order to achieve the above-mentioned objects, there is provided according to one aspect of the present invention a magnetic recording medium comprising:

20 an in-plane magnetic film used for recording, the in-plane magnetic film having a magnetization easy axis in an in-plane direction; and

25 a perpendicular magnetic film formed on the in-plane magnetic film, the perpendicular magnetic film having a magnetization easy axis oriented in a direction perpendicular to the magnetization easy axis of the in-plane magnetic film,

30 wherein a tBr of the perpendicular magnetic film is set so as not to exceed one-fifth of a tBr of the in-plane magnetic film at the maximum, where the tBr is the product of a thickness and a residual magnetization.

35 According to the present invention, since the magnetic condition of the perpendicular magnetic film is restricted within a predetermined range, the perpendicular magnetic film sufficiently functions

as an auxiliary film to the in-plane magnetic film;
thus, the magnetic recording medium can have a
composite structure that can restrain a distortion
of a reproduction waveform so as to obtain a high
5 S/N ratio.

It is sufficient that the tBr of the
perpendicular magnetic film is set so as not to
exceed 1/5 of the tBr of the in-plane magnetic film.
More preferably, the tBr of the perpendicular
10 magnetic film is set so as not to exceed 1/10 of the
tBr of the in-plane magnetic film.

Additionally, in the magnetic recording
medium according to the present invention, the
perpendicular magnetic film may have a thickness not
15 exceeding 5 nm at the maximum.

According to the present invention, the
magnetic recording medium can surely restrain the
distortion of the reproduction waveform.

Additionally, in the magnetic recording
20 medium according to the present invention, an
anisotropic magnetic field H_k of the perpendicular
magnetic film may be set at least 1.2 times as large
as an anisotropic magnetic field H_k of the in-plane
magnetic film.

According to the present invention, a
25 transition position of the perpendicular magnetic
film can be arranged to surely coincide with a
transition position of the in-plane magnetic film so
as to reduce a diamagnetic field likely to occur at
30 the transition position of the in-plane magnetic
film; this contributes to decreasing noises.

Additionally, the magnetic recording
medium according to the present invention may
further comprise a nonmagnetic spacer provided
35 between the in-plane magnetic film and the
perpendicular magnetic film.

According to the present invention, the

perpendicular magnetic film can be easily formed on the in-plane magnetic film via the nonmagnetic spacer.

5 Additionally, in the magnetic recording medium according to the present invention, the nonmagnetic spacer may have a thickness not exceeding 2 nm.

10 According to the present invention, a distance between a magnetic recording/reproducing head and the in-plane magnetic film used as a recording layer can be maintained preferably.

15 Additionally, in the magnetic recording medium according to the present invention, the perpendicular magnetic film may be formed of one of a Co-group alloy and a Co-group artificial lattice film.

 According to the present invention, the magnetic recording medium can have a more preferable perpendicular magnetic film.

20 In order to achieve the above-mentioned objects, there is also provided according to another aspect of the present invention a magnetic recording and reproducing device including:

25 a magnetic recording medium comprising:
 an in-plane magnetic film used for recording, the in-plane magnetic film having a magnetization easy axis in an in-plane direction;
 and

30 a perpendicular magnetic film formed on the in-plane magnetic film, the perpendicular magnetic film having a magnetization easy axis oriented in a direction perpendicular to the magnetization easy axis of the in-plane magnetic film,

35 wherein a tBr of the perpendicular magnetic film is set so as not to exceed one-fifth of a tBr of the in-plane magnetic film at the

maximum, where the tBr is the product of a thickness and a residual magnetization.

The magnetic recording and reproducing device according to the present invention can reduce
5 noises and exhibit an excellent reproduction waveform, and thus can perform a recording with a high density and a high sensitivity.

Other objects, features and advantages of the present invention will become more apparent from
10 the following detailed description when read in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG.1 shows a relationship between a
15 magnetic head of an in-plane recording type and magnetic recording mediums;

FIG.2 is a table showing main structural features of a perpendicular/in-plane composite medium according to a first embodiment of the
20 present invention and an in-plane single-layer medium as a comparison;

FIG.3 is a table showing magnetic characteristics of the perpendicular/in-plane composite medium according to the first embodiment
25 of the present invention and the in-plane single-layer medium, when recording and reproducing were performed to these mediums by the magnetic head;

FIG.4 is a table showing main structural features of a perpendicular/in-plane composite medium according to a second embodiment of the
30 present invention and an in-plane single-layer medium as a comparison;

FIG.5 is a table showing magnetic characteristics of the perpendicular/in-plane
35 composite medium according to the second embodiment of the present invention and the in-plane single-layer medium, when recording and reproducing were

performed to these mediums by the magnetic head;

FIG.6A is a diagram showing reproduction waveforms of a type ② of the perpendicular/in-plane composite medium and the in-plane single-layer

5 medium ① in comparison;

FIG.6B is a diagram showing reproduction waveforms of a type ③ of the perpendicular/in-plane composite medium and the in-plane single-layer medium ① in comparison;

10 FIG.7 is a table showing conditions of magnetic films when a magnetic field of the recording head is changed;

FIG.8A is a diagram showing the magnetic field of the recording head and a corresponding S/N;

15 FIG.8B is a diagram showing the magnetic field of the recording head and a corresponding transition breadth;

FIG.9 is a cross-sectional view of a main structure of a magnetic recording and reproducing device according to an embodiment of the present invention; and

20 FIG.10 is a plan view of the main structure of the magnetic recording and reproducing device shown in FIG.9.

25

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

A description will now be given, with reference to the drawings, of embodiments according to the present invention.

30 A magnetic recording medium of a composite type (hereinafter referred to as a perpendicular/in-plane composite medium) according to the present embodiments comprises an in-plane magnetic film formed on a substrate (not shown in the figures),
35 and a perpendicular magnetic film formed on the in-plane magnetic film. The in-plane magnetic film has a magnetization easy axis in an in-plane direction.

The perpendicular magnetic film has a magnetization easy axis oriented in a direction perpendicular to the substrate. This perpendicular/in-plane composite medium is preferred to have a nonmagnetic spacer inserted between the in-plane magnetic film and the perpendicular magnetic film. Accordingly, in the following description of the present embodiments, the perpendicular/in-plane composite medium having a lamination of the in-plane magnetic film, the nonmagnetic spacer and the perpendicular magnetic film is taken as an example.

Besides, in this perpendicular/in-plane composite medium, the in-plane magnetic film functions as a recording layer, and the perpendicular magnetic film formed thereon functions as an auxiliary film.

Magnetic materials such as CoCrPt and CoCrPtB can be used as the in-plane magnetic film. Generally used magnetic materials such as CoCr-group alloys can be used as the perpendicular magnetic film. However, magnetic materials such as Co-group alloys and Co-group artificial lattice films may preferably be used as the perpendicular magnetic film so that the perpendicular magnetic film has a high anisotropic magnetic field H_k . The preferable Co-group alloys include CoCrPt, TbFeCo, CoPt and FePt. The preferable Co-group artificial lattice films include Co/Pt and Co/Pd. Materials such as CoCr-group alloys can be used as the nonmagnetic spacer so as to improve a crystallinity of the perpendicular magnetic film formed thereon.

The in-plane magnetic film can be made, for example, approximately 5-20 nm in thickness, and the perpendicular magnetic film can be made approximately 1-5 nm in thickness. Especially, it is preferred that the perpendicular magnetic film is made approximately 5 nm thick at the maximum.

Additionally, in order to provide an easy understanding, the following description of the perpendicular/in-plane composite medium according to the present embodiments will be made in comparison
5 with a magnetic recording medium comprising a general in-plane magnetic film as a single layer (hereinafter referred to as an in-plane single-layer medium), the general in-plane magnetic film having a magnetization easy axis in an in-plane direction.

10 FIG.1 shows a relationship between a magnetic head 10 of an in-plane recording type and the magnetic recording mediums. In FIG.1, a recording is performed to a perpendicular/in-plane composite medium 20 according to the present
15 embodiments and an in-plane single-layer medium 30 by the magnetic head 10 with a coinciding magnetic spacing 11. Magnetic information is recorded or reproduced to/from the perpendicular/in-plane composite medium 20 according to the present
20 embodiments by the magnetic head 10 as above.

As described above, the perpendicular/in-plane composite medium 20 comprises a laminated structure of an in-plane magnetic film 21, a nonmagnetic spacer 22 and a perpendicular magnetic
25 film 23.

In the present embodiments, preconditions are set regarding the perpendicular/in-plane composite medium 20 and the in-plane single-layer medium 30 as follows. A parameter h_e of an exchange
30 interaction between magnetic particles in the films of the perpendicular/in-plane composite medium 20 and the in-plane single-layer medium 30 was 0.05. A transition breadth and an S/N ratio were calculated by recording a dye bit at each recording density.
35 The transition breadth was estimated by approximating residual magnetic components in the in-plane direction by an arc tangent function. It

is noted here that, regarding the transition breadth of the composite medium, although in-plane magnetic components of the perpendicular magnetic film are added in proportion to the thickness, it has been
5 ascertained that this addition does not influence the reduction of the transition breadth, because the perpendicular magnetic film has a low tBr (the product of the thickness and the residual magnetization). A noise in the S/N ratio was
10 calculated by integrating fluctuating components in reproduction output.

[Embodiment 1]

FIG.2 is a table showing main structural features of the perpendicular/in-plane composite
15 medium 20 according to a first embodiment and the in-plane single-layer medium 30 as a comparison.

As shown in FIG.1 and FIG.2, the perpendicular/in-plane composite medium 20 according to the present embodiment comprises the in-plane
20 magnetic film 10 nm thick, the nonmagnetic spacer 1 nm thick, and the perpendicular magnetic film 1 nm thick laminated in this order from the bottom. On the other hand, the in-plane single-layer medium 30 comprises only the in-plane magnetic film 10 nm
25 thick as a single layer. The diameter of magnetic particles in each of these films is adjusted to 5 nm. The parameter h_e of the exchange interaction between the magnetic particles is 0.05.

As for the recording and reproducing
30 magnetic head 10 shown in FIG.1, the magnetic spacing was adjusted to 24 nm, and a write head magnetic field was adjusted to 2k Oe (at the center of the medium 10 nm thick). A write gap length was adjusted to 0.2 μm , and a read gap length was
35 adjusted to 0.09 μm .

FIG.3 is a table showing magnetic characteristics of the perpendicular/in-plane

composite medium 20 according to the present embodiment and the in-plane single-layer medium 30, when recording and reproducing were performed to these mediums by the magnetic head 10.

5 Two types of the perpendicular/in-plane composite medium 20 were prepared, by forming two types of the perpendicular magnetic film, one having an anisotropic magnetic field H_k of 8k Oe, a saturation magnetization M_s of 250 emu/cc, and a tBr of 3.1 G μ m, and the other having an anisotropic magnetic field H_k of 8k Oe, a saturation magnetization M_s of 500 emu/cc, and a tBr of 6.3 G μ m.

10 FIG.3 compares changes (%) in an output V and a transition breadth πa of the two types of the perpendicular magnetic film of the perpendicular/in-plane composite medium 20 having the saturation magnetizations M_s of 250 emu/cc and 500 emu/cc (the tBr of 3.1 G μ m and the tBr of 6.3 G μ m), respectively, on the basis of the in-plane single-layer medium 30 having a tBr of 47.1 G μ m. The recording density was adjusted to 200 kfc/i.

15 Two columns on the right side of the table in FIG.3 show the output V and the transition breadth πa (percentages based on the in-plane single-layer medium 30). In these columns, the in-plane single-layer medium 30 formed only by the in-plane magnetic film represents the basis of 0%, and changes in the output V and the transition breadth πa are represented in percentages for the two types of the perpendicular/in-plane composite medium 20.

20 As a magnetic recording medium, it is preferred that the output V is large. In terms of noise reduction, the transition breadth πa is preferred to be small.

25 In this comparison, when the perpendicular magnetic film has the high tBr of 6.3, it can be ascertained that the output V decreases remarkably,

compared to the perpendicular magnetic film having the tBr of 3.1 G μ m. To the contrary, it can be ascertained that the transition breadth πa increases, when the tBr is high.

5 Accordingly, it is understood that the tBr of the perpendicular magnetic film needs to be restricted low.

10 A group including inventors of the present invention has ascertained that the tBr of the perpendicular magnetic film is preferred to be set so as not to exceed 1/5 of the tBr of the in-plane magnetic film. More preferably, the tBr of the perpendicular magnetic film is set so as not to exceed 1/10 of the tBr of the in-plane magnetic film.

15 That is, when the tBr of the perpendicular magnetic film is high, the transition breadth expands due to a magnetostatic interaction to the in-plane magnetic film. Thus, it is important that the magnetostatic interaction is restricted to a moderate degree. For that purpose, it is effective to decrease the tBr of the perpendicular magnetic film, and to insert the nonmagnetic spacer approximately 1 nm thick. Since the thickness of the nonmagnetic spacer influences the magnetic
25 spacing to the magnetic head, it is preferred that the thickness of the nonmagnetic spacer is approximately 2 nm at the thickest. From the same point of view, it is preferred that the thickness of the perpendicular magnetic film is so designed not
30 to exceed 5 nm.

[Embodiment 2]

FIG.4 is a table showing main structural features of the perpendicular/in-plane composite medium 20 according to a second embodiment and the
35 in-plane single-layer medium 30 as a comparison.

As shown in FIG.4, the perpendicular/in-plane composite medium 20 according to the present

second embodiment comprises the in-plane magnetic film 5 nm thick which is thinner than the first embodiment shown in FIG.2. The nonmagnetic spacer is 1 nm thick, and the perpendicular magnetic film is 1 nm thick, as in the first embodiment.

In the present second embodiment, the in-plane single-layer medium 30 comprises only the in-plane magnetic film 6 nm thick as a single layer. The diameter of magnetic particles in each of these films is adjusted to 5 nm, as in the first embodiment shown in FIG.2. The parameter h_e of the exchange interaction between the magnetic particles is 0.05, also as in the first embodiment.

Also, in the present second embodiment, the conditions regarding the magnetic head 10 are changed from the first embodiment. Specifically, the magnetic spacing was changed to 17 nm, and the write head magnetic field was changed to 7.5k Oe (at the center of the medium 6 nm thick). The write gap length was adjusted to 0.15 μm , and the read gap length was adjusted to 0.05 μm .

FIG.5 is a table showing magnetic characteristics of the perpendicular/in-plane composite medium 20 according to the present embodiment and the in-plane single-layer medium 30, when recording and reproducing were performed to these mediums by the magnetic head 10.

As shown in FIG.5, a plurality of types of the perpendicular/in-plane composite medium 20 were prepared, by forming a plurality of types of the perpendicular magnetic film having the saturation magnetizations M_s of 600 emu/cc and 200 emu/cc (the tBr of 7.5 $G\mu\text{m}$ and the tBr of 2.5 $G\mu\text{m}$), in comparison with the in-plane single-layer medium 30 having the tBr of 56.5 $G\mu\text{m}$.

In FIG.5, in types ② and ③ of the perpendicular/in-plane composite medium 20, the

perpendicular magnetic film and the in-plane magnetic film have coinciding transition positions. On the other hand, in types ④ and ⑤ of the perpendicular/in-plane composite medium 20, the perpendicular magnetic film and the in-plane magnetic film have transition positions not coinciding with each other.

In the present embodiment, influences to a reproduction (output) waveform and an S/N were ascertained, depending on whether or not the perpendicular magnetic film and the in-plane magnetic film have the coinciding transition positions.

In the present second embodiment, the four types ②, ③, ④ and ⑤ of the perpendicular/in-plane composite medium 20 were prepared. ① is the in-plane single-layer medium 30 as a comparison.

The transition positions of the in-plane magnetic films and the perpendicular magnetic films in these four types of the perpendicular/in-plane composite mediums were adjusted by varying the anisotropic magnetic fields H_k of the perpendicular magnetic films.

In FIG.5, the types ② and ③ of the perpendicular/in-plane composite medium are cases, in which the transition positions coincide with each other. The type ④ is a case in which the transition positions do not coincide with each other by one magnetic particle (approximately 5 nm). The type ⑤ is a case in which the transition positions do not coincide with each other by four magnetic particles (approximately 21 nm).

The group including the inventors of the present invention has ascertained that in order to prevent the state in which the transition position of the perpendicular magnetic film does not coincide with the transition position of the in-plane

magnetic film, the anisotropic magnetic field H_k of the perpendicular magnetic film needs to be at least 1.2 times as large as the anisotropic magnetic field H_k of the in-plane magnetic film. Thus, the transition position of the perpendicular magnetic film can be arranged to coincide with the transition position of the in-plane magnetic film by adjusting the intensity of the anisotropic magnetic field H_k of the perpendicular magnetic film. Besides, in the present second embodiment, the recording density was adjusted to 460 kfc/i.

According to FIG.5, with respect to the type ③ in which the transition position of the perpendicular magnetic film coincides with the transition position of the in-plane magnetic film, the S/N increases by 15.1, whereas the output decreases by 6.3%, compared to the in-plane single-layer medium 30 ① as a comparison. Differentials in S/N (from the S/N of the in-plane single-layer medium 30 ①) shown in the rightmost column in the table shown in FIG.5 can be regarded as a comprehensive evaluation for each of the types of the perpendicular/in-plane composite medium 20, on the basis of the in-plane single-layer medium 30 ① as a comparison. According to this comprehensive evaluation, the type ③ of the perpendicular/in-plane composite medium provides a remarkable noise reduction despite the decreased output V , with the S/N differential of +1.2 dB from the in-plane single-layer medium 30.

In addition, regarding the types ② and ③ of the perpendicular/in-plane composite medium in which the transition positions coincide with each other, setting the t_{Br} of the perpendicular magnetic film so as not to exceed $1/5$ of the t_{Br} of the in-plane magnetic film can achieve a high S/N ratio.

The t_{Br} of the perpendicular magnetic film

of the type ③ of the perpendicular/in-plane composite medium is 2.5, and the tBr of the in-plane magnetic film thereof is 56.5, where

- (2.5/56.5) = < (1/5) stands. The tBr of the
5 perpendicular magnetic film of the type ② of the perpendicular/in-plane composite medium is 7.5, where (7.5/56.5) = < (1/5) also stands.

- Accordingly, the type ② of the perpendicular/in-plane composite medium obtains an
10 S/N differential of +0.9 dB from the in-plane single-layer medium 30 ①. However, in order to obtain an S/N ration as high as the type ③ of the perpendicular/in-plane composite, the tBr of the perpendicular magnetic film needs to be designed so
15 as not to exceed 1/10 of the tBr of the in-plane magnetic film.

- Besides, regarding the types ④ and ⑤ of the perpendicular/in-plane composite medium, since the tBr of the perpendicular magnetic film is
20 designed so as not to exceed 1/10 of the tBr of the in-plane magnetic film, these types ④ and ⑤ gain a good evaluation in comparison with the in-plane single-layer medium 30 ①, but not so excellent as the type ③.

- 25 In order to achieve the suitable perpendicular/in-plane composite medium 20, the tBr of the perpendicular magnetic film is preferred to be restricted to a predetermined value lower than the tBr of the in-plane magnetic film, and the
30 transition position of the perpendicular magnetic film is preferred to be arranged to coincide with the transition position of the in-plane magnetic film. It is inferred that, by arranging these transition positions to coincide with each other,
35 the magnetization of the perpendicular magnetic film functions so as to cause a return current of a magnetic field at the transition position of the in-

plane magnetic film. This reduces a diamagnetic field at the transition position of the in-plane magnetic film.

It is noted that, regarding the types ② and ③ of the perpendicular/in-plane composite medium, the anisotropic magnetic field H_k of the perpendicular magnetic film is 1.2 times or more as large as the anisotropic magnetic field H_k of the in-plane magnetic film.

FIG.6A is a diagram showing reproduction waveforms of the type ② of the perpendicular/in-plane composite medium and the in-plane single-layer medium ① in comparison. FIG.6B is a diagram showing reproduction waveforms of the type ③ of the perpendicular/in-plane composite medium and the in-plane single-layer medium ① in comparison.

In the type ③ of the perpendicular/in-plane composite medium having the low tBr of the perpendicular magnetic film shown in FIG.6B, a distortion of the reproduction waveform due to the presence of the perpendicular magnetic film is restricted to a lower degree, compared to the type ② of the perpendicular/in-plane composite medium having the high tBr of the perpendicular magnetic film shown in FIG.6A.

In the perpendicular/in-plane composite medium according to the present embodiment, the transition positions can be adjusted by setting the anisotropic magnetic field H_k of the perpendicular magnetic film, even when the magnetic field of the recording head is changed, as shown in FIG.7. Accordingly, the perpendicular/in-plane composite medium exhibits a high S/N as shown in FIG.8A, and has a decreased transition breadth as shown in FIG.8B.

The heretofore-described perpendicular/in-plane composite medium according to the present

embodiments can be provided as a magnetic recording medium with a high recording density that can obtain a high S/N ratio, in which the perpendicular magnetic film and the in-plane magnetic film are
5 combined so as to restrain the occurrence of noises, while resting the distortion of the reproduction waveform.

Besides, regarding the above-described perpendicular/in-plane composite medium according to
10 the present embodiments, the same results as above can be obtained in a simulation using a Micromagnetic model employing a Landau-Lifshitz-Gilbert equation. In this simulation, an analytic expression by Karlqvist assuming a ring head can be
15 used for the magnetic field of the magnetic head, and a reciprocity theorem can be used for the reproduction output.

Next, a description will be given, with reference to FIG.9 and FIG.10, of a magnetic
20 recording and reproducing device according to an embodiment of the present invention. FIG.9 is a cross-sectional view of a main structure of the magnetic recording and reproducing device according to the present embodiment. FIG.10 is a plan view of
25 the main structure of the magnetic recording and reproducing device according to the present embodiment.

As shown in FIG.9 and FIG.10, the magnetic recording and reproducing device mainly comprises a
30 housing 113 including a motor 114, a hub 115, a plurality of magnetic recording mediums 116, a plurality of recording and reproducing heads 117, a plurality of suspensions 118, a plurality of arms 119, and an actuator unit 120. The magnetic
35 recording mediums 116 are mounted to the hub 115 revolved by the motor 114. Each of the recording and reproducing head 117 is a recording and

reproducing head of a composite type comprising a reproducing head, such as an MR head or a GMR head, and a recording head, such as an inductive head. Each of the recording and reproducing head 117 is
5 mounted to an end of the corresponding arm 119 via the suspension 118. The arms 119 are driven by the actuator unit 120. The magnetic recording and reproducing device has a well-known basic structure; therefore, the basic structure will not be described
10 in detail in this description.

The magnetic recording and reproducing device according to the present embodiment is characterized by the magnetic recording mediums 116. Each of the magnetic recording mediums 116 has the
15 arrangement of, for example, the type ③ of the perpendicular/in-plane composite medium described above with reference to FIG.5. The number of the magnetic recording mediums 116 is not limited to three, but may be one, two, four or more.

20 The basic structure of the magnetic recording and reproducing device is not limited to the structure shown in FIG.9 and FIG.10. The magnetic recording mediums used in the present invention is not limited to a magnetic disk.

25 The present invention is not limited to the specifically disclosed embodiments, and variations and modifications may be made without departing from the scope of the present invention.

The present application is based on
30 Japanese priority application No. 2001-116020 filed on April 13, 2001, the entire contents of which are hereby incorporated by reference.